REPAIR

Betongspackel

Cement based flexible filer that stays workable for along time, for use on concrete surfaces indoors and outdoors. Used for filling pores and joins from casting, as well as for repairing stairs, balconies etc. where there are no special requirements for the repair material. The mix stays workable for along time, making it especially suitable for time-consuming repairs. Intended for layers up to 15 mm thick.

Work description

The substrate must be clean and free of dust, damaged concrete, grease or other substances that might weaken adhesion. For best results, treat the substrate with Bemix Korrohäft. With rough surfaced-substrates it is usually sufficient to pre-water the surface so that it is damp but not saturated. A 25 kg sack of cement is mixed with 5.5-6.5 litres of drinking water for at least five minutes into a clump-free mix. Mixing is done with a drill and mixer attachment. Vary the amount of water for the desired consistency. The temperature of the substrate and surroundings should be 5°C to 25°C. The filler is best applied with a steel trowel in layers up to 15 mm. The semi-hardened filler can be cut and shaped. The product does not need after treatment but should be protected from sun and wind for the first 24 hours.

Technical data

Cement type	CEMII/ALL 42,5R
Material consumption	1.8 kg/mm/m²
Time workable	About 2 hours
Max layer thickness	15 mm
Maximum Aggregate size	0,25 mm
Compressive strength 28 days	13 MPa

Packaging

The product is supplied as standard in 25 kg sacks (item no. 52342).

Storage

Use within 12 months from the manufacture date on the package. Assumes dry storage in unopened packaging.

Finja cannot be held responsible for information other than that given in Technical data being correct. Conditions that are outside Finja's responsibility can be e.g. handling, treatment, working methods, possible reactions with other materials and local conditions at the storage or workplace. For current information always refer to www.finja.se

